

COLOR AVAILABLE

› Refer to Stock Service Color Card

INDUSTRIAL FINISHING

- After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

CARE INSTRUCTION



Hand Wash

Any solvent
except
tetrachloroethylene

Iron low



Do not bleach



Dry Flat

COLOR FASTNESS (AVERAGE VALUES)

| | Dry rubbing | Wet rubbing | Wash fastness |
|--------|-------------|-------------|---------------|
| Light | 4 | 4 | 4 |
| Medium | 4 | 3 | 4 |
| Dark | 3 | 2/3 | 3 |

TECHNICAL INFORMATION

| | |
|---------------|---------|
| Dyeing method | hanks |
| Knot type | splicer |
| Pilling | 3.5 |

KETTLE SIZE
(Kg.)

| |
|-----|
| 30 |
| 40 |
| 80 |
| 200 |

CERTIFICATION



SUGGESTED GAUGE

10gg

NOTES:

- Might occur bleeding in designs with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- For minimum production quantities and customers' own colors please contact our sales representative or write us to essentials@incatops.com.
- Minimum for dark colors subject to revision.