


COLOR AVAILABLE

➤ Refer to Stock Service Color Card

INDUSTRIAL FINISHING

- After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.



COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	4	3	4
Dark	3	2/3	3

TECHNICAL INFORMATION		KETTLE SIZE (Kg.)	CERTIFICATION	SUGGESTED GAUGE
Dyeing method	hanks	30		10gg
Knot type	splicer	40		
Pilling	3.5	80		
		200		

NOTES:


- Might occur bleeding in designs with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- For minimum production quantities and customers' own colors please contact our sales representative or write us to essentials@incatops.com.
- Minimum for dark colors subject to revision.

COLOR AVAILABLE

➤ Refer to Stock Service Color Card

INDUSTRIAL FINISHING

- After Knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.



COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	4	3	4
Dark	3	2/3	3

TECHNICAL INFORMATION

Dyeing method	hanks
Knot type	splicer
Pilling	3.5

KETTLE SIZE
(Kg.)

hanks	tops
30	50
40	100
80	200
200	

CERTIFICATION



SUGGESTED GAUGE

12gg ~ 10gg

NOTES:

- Might occur bleeding in designs with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- For minimum production quantities and customers' own colors please contact our sales representative or write us to essentials@incatops.com.
- Minimum for dark colors subject to revision.

COLOR AVAILABLE

 Refer to Stock Service Color Card

INDUSTRIAL FINISHING

- After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

CARE INSTRUCTION



Hand Wash

Any solvent
except
tetrachloroethylene

Iron low



Do not bleach



Dry Flat

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	4	3	4
Dark	3	2/3	3

TECHNICAL
INFORMATION

Dyeing method	hanks
Knot type	splicer
Pilling	3

KETTLE SIZE
(Kg.)

30
40
80
200

CERTIFICATION

SUGGESTED
GAUGE

3gg

NOTES:

- Might occur bleeding in designs with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- For minimum production quantities and customers' own colors please contact our sales representative or write us to essentials@incatops.com.
- Minimum for dark colors subject to revision.